

## Cylinlock® 94953

### Product Description

**Hernon® Cylinlock® 94953** is a high temperature, high strength anaerobic adhesive designed to retain and seal cylindrical assemblies. This compound will cure on metallic or non-metallic substrates and is suitable for exposure to most solvents.

### Typical Applications

- Heat exchanger tubes
- Engine cylindrical liners
- Brazed or soldered joints

### Typical Properties (Uncured)

Property	Value
Resin	Dimethacrylate ester
Appearance	Green- fluorescent liquid
Viscosity @ 25°C, cP	5000-8000
Specific gravity	1.13
Flash point	See SDS

### Typical Cured Performance

Compressive Shear Strength  
Tested at RT, on steel pins and collars according to ASTM D4562.


Cure Conditions	Shear Strength, N/mm <sup>2</sup> (psi)
24 hours at 22°C	≥ 10.3 (≥ 1500)

### Typical Environmental Resistance

Cured for 1 week @ 22°C  
Shear Strength,  
Steel Pins and Collars

#### Hot Strength

Tested at temperature.



### Chemical/Solvent Resistance

Aged under condition indicated - Tested at 72°F (22°C).

Chemical/Solvent	Temperature	% of Initial Strength
	(°C)	1000 hours
Water Glycol 50/50	87	54
Brake fluid	22	64
Ethanol	22	48
Unleaded Gasoline	22	66
Motor Oil	125	>100
Acetone	22	75

### General Information

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.**

**For safe handling information on this product, consult the Safety Data Sheet (SDS).**

Where aqueous washing systems are used to clean the surfaces before bonding, it is important to check for compatibility of the washing solution with the adhesive. In some case these aqueous washes can affect the cure and performance of the adhesive.

This product is not normally recommended for use on plastics (particularly thermoplastic materials where stress cracking of the plastic could result). It is recommended to confirm compatibility of the product with such substrates.

#### Directions for Use

For best results, clean all surfaces (external and internal) with a **Hernon®** cleaning solvent and allow to dry. If the material is an inactive metal or the cure speed is to slow, apply **Primer 49 or 50** and allow to dry.

# Hernon® Technical Data Sheet

## Cylinlock® 94953

---

**For Slip Fitted Assemblies**, apply adhesive around the leading edge of the pin and the inside of the collar and use a rotating motion during assembly to ensure good coverage.

**For Press Fitted Assemblies**, apply adhesive thoroughly to both bond surfaces and assemble at high press on rates.

**For Shrink Fitted Assemblies** the adhesive should be coated onto the pin, the collar should then be heated to create sufficient clearance for free assembly.

Parts should not be disturbed until sufficient handling strength is achieved.

### Disassembly and Cleanup

To aid in disassembly anaerobic compounds can be weakened by heating to at least 500°F (260°C). Once disassembled, cured adhesive can be removed with a solvent.

### Storage

**Cylinlock® 94953** should be stored refrigerated in unopened containers at a temperature of 40°F ± 5°F. As the product is very active, it is recommended to shake the product container for three minutes every week.

To prevent contamination of unused material, do not return any material to its original container.

### Dispensing Equipment

**Hernon®** offers a complete line of semi and fully automated dispensing equipment. Contact **Hernon® Sales** for additional information.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING, INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high-performance adhesives and sealants is registered to the ISO 9001 Quality Standard.