

Tuffbond[®] 316

Product Description

Hernon[®] Tuffbond[®] 316 is a two component, room temperature cure system. By changing the ratio of resin and hardener, the cured adhesive can change from a tough and flexible to a hard and rigid system.

Tuffbond[®] 316 is recommended for bonding metal, glass, wood, concrete, and rubber, and can be used for potting and encapsulation of electrical and electronic components.

Typical Applications

- Tank lining
- Chemical resistant flooring
- Marine coating
- Underwater coating
- Potting electronic boards
- Encapsulating electrical and electronic components

Product Benefits

- Excellent resistance to organic acids and bases
- Good mechanical properties
- Outstanding resistance to abrasion
- Low temperature cure – Non-critical mixing

Typical Properties (Uncured)

Property	Part A	Part B
Base	Epoxy	Amine
Appearance	Black	Amber
Viscosity at 25°C, cP	11,000 – 20,000	8,000 – 15,000
Specific Gravity	1.17	0.97
Mix Ratio by Weight	100	40 to 110

Typical Properties (Cured)

Property	Value
Working Life at 22°C (100g), hours	2 to 3
Durometer Hardness, Shore D	70-75 (1:1 mix)
Shear Strength G/B Steel, 24 hr cure at 22°C, psi	2000 - 3500

General Information

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Storage

Tuffbond[®] 316 should be stored in a cool, dry location in unopened containers at a temperature between 45°F to 85°F (7°C to 29°C) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused material, do not return any material to its original container.

Dispensing Equipment

Hernon[®] offers a complete line of semi and fully automated dispensing equipment. Contact **Hernon[®] Sales** for additional information.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING[®], INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high-performance adhesives and sealants is registered to the ISO 9001 Quality Standard.