

Dissipator[®] 745D

Product Description

Hernon[®] Dissipator[®] 745D is a thermally conductive room temperature cure adhesive that is designed for bonding electrical components to heat sink with a controlled gap.

Dissipator[®] 745D, through a special shimming property, insulates the component electrically while allowing thermal conductivity. This special shimming feature produces a constant gap of 0.005 in. to 0.006 in. between components.

Product Benefits

- No mixing required (eliminates errors in mixing ratio)
- Room temperature cure. No heat required.
- Eliminates screws and rivets for assembly.
- Eliminates the air space between components.
- High k factor for heat conductive application

Typical Properties (Uncured)

Property	Value
Chemical type	Modified acrylic
Appearance	Light blue paste
Viscosity at 77°F (25°C), cP	300,000 to 800,000
Specific gravity	1.62
Flash point	See SDS

Typical Properties (Cured)

Physical Properties

Property	Value
Hardness, Shore D	70-75
Coefficient of thermal expansion, ASTM D696 (K ⁻¹)	60 x 10 ⁻⁶
Coefficient of thermal conductivity, W/(m·K)	0.927
Dielectric Constant at 1kHz	4.60
Dissipation Factor at 1kHz	0.05108
Tensile Strength, psi, ASTM D638	491.55
Modulus, psi	70,100.75
Elongation, tensile strain at break, %	1.61

Typical Curing Performance

Dissipator[®] 745D, when used with **Hernon[®] Activator 63**, fixtures at room temperature in less than five minutes.

Typical Cured Performance

Shear Strength, ISO 4587

Activator 63 applied to one surface

Cure @ 22°C	Substrates	N/mm ² (psi)
1 hour	Steel	≥ 3.4 (≥ 500)
24 hours	Steel	≥ 12.4 (≥ 1500)
24 hours	Aluminum	≥ 12.4 (≥ 1500)
72 hours	Steel	≥ 17.2 (≥2500)
72 hours	Aluminum	≥13.8 (≥2000)
72 hours	Aluminum to Epoxy glass	≥2.06 (≥300)

Typical Environmental Resistance

Cured for 72 hours @ 22°C.

steel lap-shear specimens (**Activator 63** applied to one surface), Shear Strength, ISO 4587

Chemical/Solvent Resistance

Aged under conditions indicated for 720 hours and tested at 22°C.

Chemical/Solvent	Temp (°C)	% of Initial Strength
Air	87	97
Water	87	54

General Information

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions for use

1. For best performance bond surfaces should be clean and free from grease.
2. Use applicator to apply the activator to the surface to be bonded.
3. After the solvent evaporates, the active ingredients will appear wet, and will remain active for up to 2 hours after application. Contamination of the surface before bonding should be prevented.
4. Apply adhesive to the unactivated surface.

5. Secure the assembly and wait for the adhesive to fixture (approximately 5 minutes) before any further handling. Full cure occurs in 4 to 24 hours.
6. The amount of adhesive applied to the part or heat sink should be limited to the amount necessary to fill the bond and just enough to give a small fillet.
7. The dispensing or application of the adhesive should be done as to minimize air entrapment within the bondline.
8. The successful application of this product depends on accurate dispensing on the parts to be bonded. **Hernon®** Equipment Engineers are available to assist you in selecting and implementing the appropriate dispensing equipment for your application.

Storage

Dissipator® 745D should be stored in a cool, dry location in unopened containers at a temperature between 45°F to 85°F (7°C to 29°C) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused material, do not return any material to its original container.

Dispensing Equipment

Hernon® offers a complete line of semi and fully automated dispensing equipment. Contact **Hernon® Sales** for additional information.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING, INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high-performance adhesives and sealants is registered to the ISO 9001 Quality Standard.