

## Dripstop<sup>®</sup> 920

### Product Description

**Heron<sup>®</sup> Dripstop<sup>®</sup> 920** is a general-purpose anaerobic pipe sealant which contains Teflon<sup>®</sup>. It has superior sealing and mild locking performance compared to tapes and non-hardening dopes. The properties of this Dripstop prevents galling on Stainless Steel, Aluminum, and other metal pipe fittings. **Dripstop<sup>®</sup> 920** reduces costs by eliminating leakage and increasing the assembly line speed.

**Dripstop<sup>®</sup> 920** seals to moderate pressure immediately and to 250 psig steam pressure in just 24 hours. This sealant also lubricates threads during make-up, prevents galling and assures smooth disassembly.

### UL Classification – File MH14222

Classified by Underwriters Laboratories Inc.<sup>®</sup> as to fire hazard only. 920 Pipe Sealant with Teflon<sup>®</sup>. Fire hazard is small. No flash point in liquid state. Ignition temperature 455°C (851°F). For use in devices handling gasoline, petroleum oils, natural gas (pressure not to exceed 300 psig), butane and propane not exceeding 2 in. pipe size. 29R9.

### Product Benefits

- Instant seal
- Seals against liquid and gas leaks
- Lubricates parts for easy assembly
- Prevents Galling on metal pipe threads and fittings
- Does not cure until joint is assembled
- Eliminates waste. No dripping or running
- Easy disassembly
- Single component
- Solventless and it will not crack or shrink due to solvent evaporation

### Typical Applications

- Hydraulic line fittings
- Pneumatic line fittings
- Fuel line fittings
- Fluid connections
- Steam lines up to 250 psig
- Pipe plugs

### Typical Properties (Uncured)

Property	Value
Chemical Type	Dimethacrylate Ester
Appearance	Off-White Paste
Viscosity @ 25°C, cP	300,000 – 500,000
Specific Gravity	1.33
Flash Point	See SDS
VOC Content (ASTM D2369)	1.22 lb/gal

### Typical Properties (Cured)

Property	Value
Pressure Resistance, psi	10,000
Temperature Range, °C (°F)	-55 to 204 (-65 to 400)

### Typical Cured Performance

Breakaway Torque Strength, ISO 10964  
3/8 x 24 Grade 2 Steel Nuts and Bolts

Cure Conditions	Value, in-lb
24 hours @ 95°C, Tested at 22°C	≥ 50
72 hours @ 22°C	≥ 5

### Typical Environmental Resistance

Cured for 72 hours @ 22°C  
Breakaway Torque, ISO 10964:  
3/8inch NPT steel pipe tees and plugs (degreased)

### Chemical/Solvent Resistance

Aged 720 hours at conditions indicated, tested at 22°C.

Chemical/Solvent	°C	Breakaway Torque, in-lb
Motor oil	87	150 - 210
Unleaded Gasoline	22	10 - 40
Isopropanol	22	10 - 40
Air	87	210 - 280
Distilled Water	87	20 - 70
Automatic Transmission Fluid	87	80 - 130
Brake Fluid	87	30 - 90

# Hernon® Technical Data Sheet

## Dripstop® 920

---

### General Information

**For safe handling information on this product, consult the Safety Data Sheet (SDS).**

Where aqueous washing systems are used to clean the surfaces before bonding, it is important to check for compatibility of the washing solution with the adhesive. In some case, these aqueous washes can affect the cure and performance of the adhesive.

This product is not normally recommended for use on plastics (particularly thermoplastic materials where stress cracking of the plastic could result). It is recommended to confirm compatibility of the product with such substrates.

### Directions for use

#### For Assembly

1. For best results, clean all surfaces (external and internal) with **Hernon® Cleaner 62** and allow to dry.
2. If the material is an inactive metal or the cure speed is too slow, spray with **Hernon® Primer 49 or 50** and allow to dry.
3. Apply a 360° bead of product to the leading threads of the male fitting, leaving the first thread free. Force the material into the threads to thoroughly fill the voids. For bigger threads and voids, adjust product amount accordingly and apply a 360° bead of product on the female threads also.
4. Using accepted trade practices, assemble and wrench tighten fittings until proper alignment is obtained.
5. Properly tightened fittings will seal instantly to moderate pressures. For maximum pressure resistance and solvent resistance allow the product to cure a minimum of 24 hours.

#### For Disassembly

1. Remove with standard hand tools.
2. Where hand tools do not work because of excessive engagement length or large diameters (over 1"), apply localized heat to approximately 250°C. Disassemble while hot.
3. Once disassembled, cured adhesive can be removed with **Hernon® Chemical Stripper 30**.

#### For Cleanup

1. Cured product can be removed with a combination of soaking in **Hernon® Cleaner 62** and mechanical abrasion such as a wire brush.

### Storage

**Dripstop® 920** should be stored in a cool, dry location in unopened containers at a temperature between 45°F to 85°F unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused material, do not return any material to its original container.

### Dispensing Equipment

**Hernon®** offers a complete line of semi and fully automated dispensing equipment. Contact **Hernon® Sales** for additional information.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING, INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high-performance adhesives and sealants is registered to the ISO 9001 Quality Standard.

Teflon® is a registered trademark of DuPont.